


The 9th International Concrete Conference 2016

Environment, Efficiency and
Economic Challenges for Concrete

Proceedings



Queensferry Crossing: Photo Courtesy of Transport Scotland

Sponsored by



Exhibitors



9th International Concrete Conference 2016

Environment, Efficiency and Economic Challenges for Concrete

4-6 July 2016

Dundee, Scotland, UK

Edited by

M Roderick Jones

*Director, Concrete Technology Unit
University of Dundee*

Moray D Newlands

*Senior Lecturer, Concrete Technology Unit
University of Dundee*

Judith E Halliday

*Research/Teaching Fellow, Concrete Technology Unit
University of Dundee*

Laszlo J Csetenyi

*Research/Teaching Fellow, Concrete Technology Unit
University of Dundee*

Li Zheng

*Research/Teaching Fellow, Concrete Technology Unit
University of Dundee*

Michael J McCarthy

*Reader, Concrete Technology Unit
University of Dundee*

Thomas D Dyer

*Lecturer, Concrete Technology Unit
University of Dundee*

EFFECT OF NANO-SILICA AND AGGREGATE TYPE ON PROPERTIES OF ULTRA HIGH PERFORMANCE CONCRETE

K Janković

IMS Institute

M Stojanović

S J Stanković

Vinča Institute of Nuclear Sciences

D Bojović

IMS Institute

Serbia

L Antić

ABSTRACT. The aim of this investigation is to develop ultra high performance concrete (UHPC) for multipurpose - higher mechanical and ionizing radiation protection. The effect of nano-silica replacement (2 or 5%) on the properties of UHPC was compared with the referent concrete by testing compressive and flexural strength. As nano-silica influences cement hydration and modifies the pore structure, qualitative and quantitative analysis of pores was done using a device RapidAir 457. The second objective of this paper is to evaluate the influence of different aggregates on concrete properties. Two types of aggregate were used: quartz and barite. One of the most important characteristics of the concrete for protection against gamma and X radiation is its Total Attenuation Coefficient $(\mu/\rho)_{\text{tot}}$.

Key word: Nano-silica, UHPC, Barite, Radiation protection.

Ksenija Janković, senior research fellow is Head of Laboratory for Concrete at IMS Institute, Belgrade, Serbia. Her research interests include ultra high performance concrete, utilization of by-products and recycled waste materials in concrete and concrete durability. She has published about 140 papers.

Srboljub J Stanković, MSc EE, research assistant is working in the Department of Radiation and Environmental Protection at Vinča Institute of Nuclear Sciences, University of Belgrade, Serbia. He is a PhD candidate at the School of Electrical Engineering at Belgrade University. He is especially interested in nuclear engineering, physical properties of materials, radiation protection and ionizing radiation.

Marko Stojanović, MSc CE, research assistant is working in the Laboratory for Concrete at IMS Institute. He is a PhD student at the Faculty of Civil Engineering, Subotica at Novi Sad University. His research interests are SCC and ultra high performance concrete.

Dragan Bojović, MSc CE, research assistant is working in the Laboratory for Concrete at IMS Institute. He is a PhD candidate at the Faculty of Technical Sciences at Novi Sad University. His research interests focus on ultra high performance concrete, SCC, concrete fracture and concrete quality control in situ.

Lana Antić, MSc CE is working in the Laboratory for Concrete at IMS Institute.

INTRODUCTION

Modern construction industry required building materials with improved properties. Ultra high performance concrete is one of them. Significant increases in mechanical properties of cementitious materials have been achieved by incorporating nano-silica [1]. By replacing a part of cement content with nano-silica it is possible to produce concrete with high performance and it can also reduce CO₂ emission.

Land and Stephan studied the way different nanoparticles affect cement hydration [2]. The acceleration of cement hydration was dependant on the total surface size of added nano-silica particles [3]. The pore size distribution also showed that nano-silica refined the large capillary pores, due to the combined contribution of the nano-filler effect and the pozzolanic reaction [4]. The fact that pore-size distribution was becoming finer, reduced pore volume and improved physico-mechanical properties of the mortars after the addition of nano-powders could be explained by the filler effect or the amount of hydration products of cement [5].

By adding between 3% and 10% w/w of colloidal silica suspension in the fiber-cement composites, the pullout of the fibers increased significantly [6]. Compressive strength and transport properties of UHPC also increased with the addition of nano-silica. For best performance, the optimum amount of nano-silica for cement replacement in the cement paste was 3 wt.% [7]. The results showed that up to 3% increase in the nano-silica content resulted in the increase in compressive and flexural strength of UHPC, and when the nano-silica content was more than 3% the mechanical properties decreased slightly due to agglomeration of nano-silica particles. The addition of nano-silica accelerated the hydration process. By increasing the nano-silica content the average pore diameter and porosity decreased. The microstructure was more homogenous and dense for nano-silica specimens when compared to the control specimen [8].

By using new nanomaterials higher temperatures will be allowed and hence a more efficient operation of power plants will be achieved, and the development of new energy production systems based on solar, nuclear and renewable sources will be enabled [9]. Ultra high performance concrete can be used in nuclear power plants and defensive facilities due to its dynamical behavior [10].

Barite aggregate is used to produce heavyweight concrete which is used for shielding in nuclear facilities and hospitals. Concrete with barite powder used as sand substitution in range between 0% and 25% decreased the compressive strength at 28 days just by 10% [11]. The grading curve of barite was modified by mixing process at a higher extent than for other aggregates. This influenced the properties of concrete by increasing workability, but decreasing compressive strength and the modulus of elasticity [12]. The basic characteristics of ordinary concrete and heavy-weight concrete with barite were studied for the application in shielding from gamma radiation [13, 14].

Also, one of the goals is the implementation of appropriate numerical calculations for obtaining the total mass attenuation coefficient value in the energy range 10 keV - 150 MeV of gamma and X radiation, depending on the changes in the concrete type in UHPC concrete with specially defined mechanical properties.

EXPERIMENTAL WORK

The design of ultra high performance concrete is different than ordinary concrete. High amount of fine particles is used for UHPC manufacturing. Their properties are shown in Table 1.

Table 1 Properties of powder materials and sand

	CEMENT	SILICA FUME	QUARTZ POWDER	QUARTZ SAND	BARITE SAND
SiO ₂ , %	20.51	92.52	97.54	97.54	11.13
Al ₂ O ₃ , %	6.15	0.64	0.52	0.52	2.24
Fe ₂ O ₃ , %	2.80	0.31	0.57	0.57	1.55
CaO, %	63.41	0.38	0	0	0.18
MgO, %	1.85	0.44	0	0	0
Na ₂ O, %	0.29	0.32	0	0	0.86
K ₂ O, %	0.79	0.87	0.24	0.24	0.72
SO ₃ , %	2.69	0.22	0	0	28.05
Ba, %	0	0	0	0	53.15
Cr, %	0	0	0	0	0.4
Sr, %	0	0	0	0	1.72
Specific density, kg/m ³	3100	2200	2695	2695	3770
Bulk density, kg/m ³				1650	2260

Concrete was made with ordinary Portland cement CEM I 42.5 R. Also, silica fume (SF) and nano-silica (nS) with average particle size of 7 nm were pozzolanic materials. Quartz powder (Qp) with average particle size of 50 µm and quartz sand (Qs) or barite sand (B) up to 4 mm were used as aggregate. A modified polycarboxylates based superplasticizer allowed high water reduction. Brass coated steel fibers with 8 mm length and a diameter of 0.15 mm were used (5% by volume). Six types of concrete were made with varying percent of nano-silica (0%, 2% and 5%) and aggregate type (quartz and barite). Composition of concrete mixtures are shown in Table 2.

Table 2 Concrete mixture composition, kg/m³

	K0f5	K2f5	K5f5	B0f5	B2f5	B5f5
C	950	931	902.5	950	931	902.5
SF	200	200	200	200	200	200
nS	0	19	47.5	0	19	47.5
Qp	350	350	350	335	335	335
Qs	570	570	570	0	0	0
B	0	0	0	810	810	810
Water	230	250	250	230	250	250
Superplasticizer	55	55	55	55	55	55
Fibers	390	390	390	390	390	390

NUMERICAL CALCULATIONS OF TOTAL MASS ATTENUATION COEFFICIENT

Total Mass Attenuation Coefficient $(\mu/\rho)_{tot}$ is one of the most important concrete characteristics for protection against gamma and X radiation.

The definition of Total Mass Attenuation Coefficient for mixture is given by:

$$\left(\frac{\mu}{\rho}\right)_{tot} = \sum_j w_j \cdot \left(\frac{\mu}{\rho}\right)_j \quad (1)$$

where $(\mu/\rho)_j$ and w_j are the weight fraction and mass attenuation coefficient of the constituent element j.

The numerical calculations included two steps: 1. The composition of each type of concrete from Table 2 was determined in accordance with the nomenclature of chemical elements and chemical compounds, 2. Interactive use of the XCOM program [15], where the known composition of individual types of concrete determines the total mass attenuation coefficient depending on the change of energy photon radiation.

XCOM program enables the calculation of interaction coefficients for the following processes: Compton (incoherent) and Rayleigh (coherent) scattering, photoelectric absorption, and pair production in the fields of the atomic nucleus and atomic electrons. The mean free paths between scatterings, between photo-electric absorption events, or between pair production events are the reciprocals of partial interaction coefficients. The total attenuation coefficient is calculated as the sum of the interaction coefficients for the individual processes.

RESULTS AND DISCUSSION

Samples for testing the mechanical properties were prepared in molds 4 cm × 4 cm × 16 cm by the vibration on vibro-table for 60 s. Next day, specimens were demoulded and put into water and cured up to testing.

The results of compressive strength of concrete with quartz were given in Figure 1 and for UHPC with barite aggregate were shown in Figure 2.




Figure 1 Compressive strength of UHPC with quartz aggregate




Figure 2 Compressive strength of UHPC with barite aggregate

Obtained values of flexural strength of all concrete types are shown in Table 3.

Table 3 Flexural strength of concrete, N/mm²

	K0f5	K2f5	K5f5	B0f5	B2f5	B5f5
7 days	26.1	29.4	25.0	25.0	34.0	24.8
28 days	28.0	37.4	27.3	31.1	38.9	32.0

By comparing concrete made with different aggregate it can be seen that the concrete made with barite aggregate had better results than concrete made with quartz aggregate. For compressive strength, the difference is about 4% for concrete with nano-silica and 3% for concrete without nano-silica. Flexural strength of concrete with barite sand and 5% of nano-silica is 17% higher, for UHPC without nano-silica is 11% higher, while concrete made with 2% nano-silica had only 4% higher flexural strength when compared to concrete made only with quartz aggregate.

Comparing concrete made with the same type of aggregate we can see that its compressive strength increases with the addition of nano-silica. For barite concrete, the difference is 3% for concrete with 2% nano-silica and 6% for concrete with 5% nano-silica related to UHPC without nano-silica. Concrete with quartz sand and 2% nano-silica had only 2% higher compressive strength and with 5% nano-silica had 4% greater compressive strength comparing to mixture without nano-silica. Influence of 2% nano-silica had positive effect on flexural strength. It increased 34% for quartz concrete and 25% for barite concrete. With 5% nano-silica flexural strength slightly decreased for concrete with quartz aggregate, while it slightly increased for concrete with barite aggregate when compared to UHPC without nano-silica.

Pore-size distribution was tested by RapidAir 457 device. With the increase in the nano-silica content pore-size distribution became finer. Results for concrete with barite sand are given in Table 4.

Table 4 Test results by device RapidAir 457

CONCRETE	B0f5	B2f5	B5f5
Air Content, %	3.35	3.30	2.64
Specific Surface, mm ⁻¹	24.14	30.17	68.61
Spacing Factor, mm	0.421	0.278	0.164
Void Frequency, mm ⁻¹	0.202	0.400	0.454
Average Chord Length, mm	0.166	0.133	0.058

For a selected value of the nano-silica content (2%) calculations for the mass attenuation coefficients were carried out and their dependence on energy photon radiation is shown in the Figure 3.

Larger values of mass attenuation coefficient for concrete B2 in relation to the K2 concrete due to the presence of barium (Ba) as a component of the aggregate with which the concrete B2 was made (Figure 3). Especially it can be observed the influence of the presence of barium in the concrete type B2 because it significantly increases its capability for absorption of X and gamma rays with energies below 300 keV.




Figure 3 Total mass attenuation coefficients for concrete with 2% nano-silica

CONCLUSIONS

If we compare concrete made with the same type of aggregate, it can be concluded that cement replacement with nano-silica in the amount of 2% has a positive impact on both the compressive and flexural strength. The flexural strength decreased, but the compressive strength increased when the nano-silica content was 5%.

Concrete with barite aggregate had better mechanical properties than concrete with quartz aggregate. Type of used aggregate has a much greater influence on flexural strength than on the compressive strength, e.g. for mixtures with 5% nano-silica content, concrete made with barite sand had 4% greater compressive and 17% greater flexural strength than concrete with quartz sand.

Based on the results of the corresponding graphs for Total Mass Attenuation Coefficient it can be concluded that in the range of energy of gamma and X radiation from 10 keV to 150 MeV, concrete with barite sand has greater protective power than concrete with quartz sand. From the aspect of compressive, flexural strength and radiation protection UHPC with barite sand and 2% cement replacement with nano-silica is optimal.

ACKNOWLEDGEMENTS

The work reported in this paper is a part of the research project TR 36017 supported by the Ministry of Education, Science and Technological Development, Republic of Serbia.

REFERENCES

1. SINGH L.P., KARADE S.R., BHATTACHARYYA S.K., YOUSUF M.M. and AHALAEAT S. Beneficial role of nanosilica in cement based materials – A review, *Constr Build Mater*, Vol. 47, 2013, pp. 1069–1077.
2. LAND G. and STEPHAN D. Controlling cement hydration with nanoparticles, *Cem Concr Comp*, Vol. 57, 2015, pp. 64–67.
3. LAND G. and STEPHAN D. The influence of nano-silica on the hydration of ordinary Portland cement, *J Mater Sci*, Vol. 47, 2012, pp. 1011–1017.
4. DU H., DU S. and LIU X. Durability performances of concrete with nano-silica, *Constr Build Mater*, Vol. 73, 2014, pp. 705–712.
5. OLTULU M. and SAHIN R. Pore structure analysis of hardened cement mortars containing silica fume and different nano-powders, *Constr Build Mater*, Vol. 53, 2014, pp. 658–664.
6. SANTOS S.F., De ANCHIETA RODRIGUES J., TONOLI G.H.D., De SOUZA ALMEIDA A.E.F. and SAVASTANO H. Jr. Effect of colloidal silica on the mechanical properties of fiber–cement reinforced with cellulosic fibers, *J Mater Sci*, Vol. 49, 2014, pp. 7497–7506.

7. GHAFARI E., COSTA H., JULIO E., PORTUGAL A. and DURAES L. The effect of nanosilica addition on flowability, strength and transport properties of ultra high performance concrete, *Mater Des*, Vol. 59, 2014, pp. 1–9.
8. RONG Z., SUN W., XIAO H. and JIANG G. Effects of nano-SiO₂ particles on the mechanical and microstructural properties of ultra-high performance cementitious composites, *Cem Concr Comp*, Vol. 56, 2015, pp. 25–31.
9. CHATURVEDI S. and DAVE P.N. Design process for nanomaterials, *J Mater Sci*, Vol. 48, 2013, pp. 3605–3622.
10. LAI, J, SUN, W. Dynamic behaviour and visco-elastic damage model of ultra-high performance cementitious composite, *Cem Concr Res*, 39(11), 2009, pp 1044–51
11. SAIDANI K., AJAM L. and OUEZDOU M.B. Barite powder as sand substitution in concrete: Effect on some mechanical properties, *Constr Build Mater*, Vol. 95, 2015, pp. 287–295.
12. GONZALEZ-ORTEGA M.A., CAVALARO S.H.P. and AGUADO A. Influence of barite aggregate friability on mixing process and mechanical properties of concrete, *Constr Build Mater*, Vol. 74, 2015, pp. 169–175.
13. AKKURT I., BASYIGIT C., KILINCARSLAN S., MAVI B. and AKKURT A. Radiation shielding of concretes containing different aggregates, *Cem Concr Comp*, Vol. 28, 2006, pp. 153–157.
14. AKKURT I., BASYIGIT C., KILINCARSLAN S. and MAVI B. The shielding of gamma – rays by concretes produced with barite, *Prog Nucl Energy*, Vol. 46, No. 1, 2005, pp. 1-11.
15. BERGER M.J., HUBBELL J.H., SELTZER S.M., CHANG J., COURSEY J.S., SUKUMAR R., ZUCKER, D.S. and OLSEN K. XCOM: Photon Cross Section Database (version 3.1). <http://www.nist.gov/pml/data/xcom/index.cfm>, NBSIR 87-3597. National Institute of Standards and Technology, Gaithersburg, MD, 2010.

ISBN 9780957326316



9 780957 326316